

## TECHNICAL DATA SHEET

# RILSAN® HT CSR 13

### POLYPHTALAMIDE PELLET

RILSAN® HT CSR 13 is polyphthalamide compound. It is partially produced from a renewable & sustainable source (castor oil). This black reinforced grade is designed for injection molding & is used to produce high temperature and high chemical resistance automotive fittings & quick connectors, the incorporation of carbon fiber leading to a product with same rigidity as a 30% glass fiber reinforced grade & electrostatic discharge (ESD) performance for conductive parts.

Designation : ISO 16396 - PA10T/X, CF13, M1G1HL, C16-080

#### DESIGNATION

PA10T/X-CF15

#### DELIVERY FORM

- Pellets

#### TRANSFORMATION PROCESSES

- Injection Molding

#### ADDITIVES

- Heat Stabilized
- Light Stabilized
- Release agent

### RHEOLOGICAL PROPERTIES

속성	값	테스트 표준
Melt volume flow rate (MVR), 275°C / 2.16 kg (527°F / 4.4 lb)	12 cm <sup>3</sup> /10min	ISO 1133
Shrinkage, Parallel (t+24h)	0.3 %	ISO 294-4
Shrinkage, Normal (t+24h)	0.6 %	ISO 294-4

### MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	테스트 표준
Charpy unnotched impact strength, 23°C (73°F)	- / 40 kJ/m <sup>2</sup>	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / 32 kJ/m <sup>2</sup>	ISO 179 1eU
Tensile modulus, 23°C (73°F), 1 mm/min	7600 / 7600 MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 5 kJ/m <sup>2</sup>	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 4 kJ/m <sup>2</sup>	ISO 179 1eA

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

# RILSAN® HT CSR 13

속성	값	테스트 표준
Heat deflection temperature, 0.45 MPa	235 °C	ISO 75-1/-2
Heat deflection temperature, 1.8 MPa	195 °C	ISO 75-1/-2
Melting temperature, 10°C/min	255 °C	ISO 11357-1/-3

## OTHER PROPERTIES

속성	값	테스트 표준
Bio-based carbon content, Measured	52 %	ASTM D6866
Specific gravity, 23°C (73°F)	1.15 g/cm <sup>3</sup>	ISO 1183-1

## PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 26 kg / 55 lb bags

## SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 270°C / 290°C / 310°C (520°F / 555°F / 590°F)
- Typical mold temperature - Injection molding: 90-110°C (195-230°F)
- Drying time and temperature: 100-110°C (210-230°F) / 4-8 hours

## SPECIAL CHARACTERISTICS

- Bio-based
- Electrostatic discharge (ESD)

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**