

## TECHNICAL DATA SHEET

# RILSAN® PA11 D40 NAT

## POLYAMIDE 11 POWDER

RILSAN® D40 NAT is a polyamide 11 powder obtained from renewable resources with an average diameter of 27 - 31 µm. RILSAN® D is a range of high performance fine polyamide powders used as multifunctional additives in coatings and varnishes. The introduction of RILSAN® polyamide powders in formulations is easy thanks to their good dispersion capacity, their reduced Impact on rheology and their low density. RILSAN® polyamide powders are surface modifiers, specifically designed for texture creation. Abrasion, scratch, impact resistances and flexibility of coatings, inks and varnishes can be significantly improved using RILSAN® polyamide powders.

### DESIGNATION

PA11

### DELIVERY FORM

- Powder

### TRANSFORMATION PROCESSES

- Formulation ingredients

### ADDITIVES

- Heat Stabilized

속성	값	테스트 표준
Vicat softening temperature, 50N at 50°C/h	160 °C	ISO 306
Melting temperature, 10°C/min	183-188 °C (366.8 °F)	ISO 11357-1/-3

## THERMAL PROPERTIES ELECTRICAL PROPERTIES

속성	DRY / COND VALUE*	테스트 표준
Surface resistivity, 23°C (73,4°F)	- / 1.0E+14 ohm/sq	IEC 62631-3-2
Volumic (transversal) resistivity, 23°C (73,4°F)	- / 1.0E+12 ohm/m	IEC 62631-3-1
Dielectric Strength, 23°C (73,4°F)	/ 30 kV/mm	IEC 60243-1

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

## OTHER PROPERTIES

속성	값	테스트 표준
Median particles (D50)	27-31 µm	ISO 13319
Water absorption, Saturated in water at 23°C (73°F)	1.9 %	ISO 62
Apparent density, Non compacted	0.37	ISO 1068
Specific gravity of coating, 20°C (68°F)	1.04 g/cm³	ISO 1183-1

## PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 21 kg / 44 lb bags

# RILSAN® PA11 D40 NAT

## SHELF LIFE

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## SPECIAL CHARACTERISTICS

- Bio-based

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**