

TECHNICAL DATA SHEET

RILSAN® PA11 D80 NAT

POLYAMIDE 11 POWDER

RILSAN® D80 NAT is a polyamide 11 powder obtained from renewable resources with an average diameter of 95 - 105µm. RILSAN® D is a range of high performance fine polyamide powders used as multifunctional additives in coatings and varnishes.

The introduction of RILSAN® polyamide powders in formulations is easy thanks to their good dispersion capacity, their reduced impact on rheology and their low density.

RILSAN® polyamide powders are surface modifiers, specifically designed for texture creation.

Abrasion, scratch, impact resistances and flexibility of coatings, inks and varnishes can be significantly improved using RILSAN® polyamide powders.

Designation

- PA11

MAIN APPLICATIONS

- Coating Additives - Coil Coating
- Graphic Arts Additives - Ink/OPV/Paper

Delivery Form

- Powder

Transformation Processes

- Formulation ingredients

Additives

- Heat Stabilized

THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	183-188 °C	ISO 11357-1/-3

OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Median particles (D50)	95-105 µm	ISO 13319
Water absorption, 24h	≤ 1 %	ISO 62
Apparent density, Non compacted	0.47	ISO 1068
Specific gravity of coating, 20°C (68°F)	1.04 g/cm ³	ISO 1183-1

SHELF LIFE

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

SPECIAL CHARACTERISTICS

- Bio-based

Headquarter: Arkema France
 420, rue d'Estienne d'Orves
 92705 Colombes Cedex – France
 T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790