

# TECHNICAL DATA SHEET RILSAN® PA11 ES BLACK 710 MAC

### **POLYAMIDE 11 POWDER**

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® ES range is designed for coating metal parts using the electrostatic spraying process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

#### Designation

• PA11

#### MAIN APPLICATIONS

- · Automotive/Truck Shaft Coating
- Automotive/Truck Automotive Coating

#### **Delivery Form**

Powder

#### **Transformation Processes**

· Electrostatic spraying

#### Additives

· Heat Stabilized

#### MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Hardness, Persoz, 23°C (73°F)	- / 270	ISO 1522
Hardness, Shore D, 23°C (73°F)	- / 72	ISO 868
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 36 mg	ISO 9352

<sup>\*</sup>DRY: Dry As Molded (DAM) if pellet / Dry if powder. COND: Conditionned.

#### THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	183-188 °C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181 °C (357.8 °F)	ISO 306



## RILSAN® PA11 ES BLACK 710 MAC

#### **OTHER PROPERTIES**

PROPERTIES	VALUE	TEST STANDARD
Apparent density, Non compacted	0.43	ISO 1068
Apparent density, Compacted	0.63	ISO 1068
Approximate RAL number	9011	
Covering efficiency (120 µm)	0.14 kg/m²	Internal Arkema
Median particles (D50)	30 μm	ISO 13320
Particle Size Distribution (PSD) (Fine particles < 20 µm)	20 %	ISO 13320
Particle Size Distribution (PSD) (Coarse particles > 100 μm)	1 %	ISO 13320
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Specific gravity of coating, 20°C (68°F)	1.35 g/cm³	ISO 1183-1
Water absorption, 24h	≤ 1 %	ISO 62

#### 賞味期限

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

#### SPECIAL CHARACTERISTICS

Bio-based

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

