

TECHNICAL DATA SHEET RILSAN® PA11 ES BLACK 710 MAC

POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® ES range is designed for coating metal parts using the electrostatic spraying process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

DESIGNATION

PA11

DELIVERY FORM

Powder

TRANSFORMATION PROCESSES

· Electrostatic spraying

ADDITIVES

· Heat Stabilized

MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	테스트 표준
Hardness, Persoz, 23°C (73°F)	- / 270	ISO 1522
Hardness, Shore D, 23°C (73°F)	- / 72	ISO 868
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 36 mg	ISO 9352

^{*}DRY: Dry As Molded (DAM) if pellet / Dry if powder. COND: Conditionned.

속성	값	테스트 표준
Melting temperature, 10°C/min	183-188 °C (366.8 °F)	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181 °C	ISO 306



RILSAN® PA11 ES BLACK 710 MAC

OTHER PROPERTIES

속성	값	테스트 표준
Apparent density, Non compacted	0.43	ISO 1068
Apparent density, Compacted	0.63	ISO 1068
Approximate RAL number	9011	
Covering efficiency (120 µm)	0.14 kg/m²	Internal Arkema
Median particles (D50)	30 µm	ISO 13320
Particle Size Distribution (PSD) (Fine particles < 20 μm)	20 %	ISO 13320
Particle Size Distribution (PSD) (Coarse particles > 100 μm)	1 %	ISO 13320
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Specific gravity of coating, 20°C (68°F)	1.35 g/cm ³	ISO 1183-1
Water absorption, 24h	≤ 1 %	ISO 62

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

• 851 kg / 1870 lb rigid containers

SHELF LIFE

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

SPECIAL CHARACTERISTICS

Bio-based

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

