

## TECHNICAL DATA SHEET

# RILSAN® PA11 ES WHITE 1464 EC

## POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® ES range is designed for coating metal parts using the electrostatic spraying process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

### DESIGNATION

PA11

### MAIN APPLICATIONS

- Water Fluid Coating - Water Accessories
- Powder Coating - Undergarment
- Powder Coating- Wire Goods
- Coating Additives - Wood
- Coating Additives - Coil Coating

### DELIVERY FORM

- Powder

### TRANSFORMATION PROCESSES

- Electrostatic spraying

### ADDITIVES

- Heat Stabilized

## MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Hardness, Persoz, 23°C (73°F)	- / 270	ISO 868
Hardness, Shore D, 23°C (73°F)	- / 71	ISO 868
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 10 mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditioned.

## THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	183-188 °C (366.8 °F)	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181 °C	ISO 306

# RILSAN® PA11 ES WHITE 1464 EC

## OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Apparent density, Non compacted	0.44	ISO 1068
Apparent density, Compacted	0.62	ISO 1068
Approximate RAL number	9016	
Covering efficiency (120 µm)	0.14 kg/m <sup>2</sup>	Internal Arkema
Median particles (D50)	30 µm	ISO 13320
Particle Size Distribution (PSD) (Fine particles < 20 µm)	20 %	ISO 13320
Particle Size Distribution (PSD) (Coarse particles > 100 µm)	1 %	ISO 13320
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Specific gravity of coating, 20°C (68°F)	1.1 g/cm <sup>3</sup>	ISO 1183-1
Water absorption, 24h	≤ 1 %	ISO 62

## PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 20 kg / 44 lb bags

## SHELF LIFE

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## SPECIAL CHARACTERISTICS

- Bio-based

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

**ARKEMA**