

TECHNICAL DATA SHEET RILSAN® PA11 ES WHITE 1464 EC

POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® ES range is designed for coating metal parts using the electrostatic spraying process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

DESIGNATION

PA11

MAIN APPLICATIONS

- · Water Fluid Coating Water Accessories
- Powder Coating Undergarment
- Powder Coating- Wire Goods
- · Coating Additives Wood
- · Coating Additives Coil Coating

DELIVERY FORM

Powder

TRANSFORMATION PROCESSES

· Electrostatic spraying

ADDITIVES

· Heat Stabilized

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Hardness, Persoz, 23°C (73°F)	- / 270	ISO 868
Hardness, Shore D, 23°C (73°F)	- / 71	ISO 868
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 10 mg	ISO 9352

^{*}DRY: Dry As Molded (DAM) if pellet / Dry if powder. COND: Conditionned.

THERMAL PROPERTIES

プロバティ	価値	テスト基準
Melting temperature, 10°C/min	183-188 °C (366.8 °F)	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181 °C	ISO 306



RILSAN® PA11 ES WHITE 1464 EC

OTHER PROPERTIES

プロパティ	価値	テスト基準
Apparent density, Non compacted	0.44	ISO 1068
Apparent density, Compacted	0.62	ISO 1068
Approximate RAL number	9016	
Covering efficiency (120 µm)	0.14 kg/m²	Internal Arkema
Median particles (D50)	30 μm	ISO 13320
Particle Size Distribution (PSD) (Fine particles < 20 μ m)	20 %	ISO 13320
Particle Size Distribution (PSD) (Coarse particles > 100 μm)	1 %	ISO 13320
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Specific gravity of coating, 20°C (68°F)	1.1 g/cm³	ISO 1183-1
Water absorption, 24h	≤ 1 %	ISO 62

包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

20 kg / 44 lb bags

賞味期限

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

SPECIAL CHARACTERISTICS

Bio-based

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

