

TECHNICAL DATA SHEET

RILSAN® PA11 ESY BLUE 7414

POLYAMIDE 11 POWDER

RILSAN® electrostatic spray powders are thermoplastic polyamides obtained from renewable resources.

Outstanding characteristics: abrasion resistance, corrosion resistance, impact resistance, sound reduction, flexibility, low coefficient of friction.

DESIGNATION

PA11

DELIVERY FORM

- Powder

TRANSFORMATION PROCESSES

- Electrostatic spraying

ADDITIVES

- Heat Stabilized

MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	테스트 표준
Hardness, Persoz, 23°C (73°F)	- / 270	ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 17 mg	ISO 9352

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.

COND: Conditionned.

속성	값	테스트 표준
Melting temperature, 10°C/min	183-188 °C (366.8 °F)	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181 °C	ISO 306

OTHER PROPERTIES

속성	값	테스트 표준
Median particles (D50)	30 µm	ISO 13320
Water absorption, 24h	≤ 1 %	ISO 62
Approximate RAL number	5010	
Covering efficiency (100 µm)	0.20 kg/m ²	Internal Arkema
Apparent density, Non compacted	0.44	ISO 1068
Apparent density, Compacted	0.62	ISO 1068
Particle Size Distribution (PSD) (Fine particles < 20 µm)	20 %	ISO 13320
Particle Size Distribution (PSD) (Coarse particles > 100 µm)	1 %	ISO 13320
Specific gravity of coating, 20°C (68°F)	1.18 g/cm ³	ISO 1183-1
Salt spray test	Good adhesion after 2000 hours	ISO 9227

RILSAN® PA11 ESY BLUE 7414

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 21 kg / 44 lb bags

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

SPECIAL CHARACTERISTICS

- Bio-based

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA