

TECHNICAL DATA SHEET RILSAN® PA11 ESY GREY 7280

POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® ESY range is designed for coating metal parts using the electrostatic spraying process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

Designation

• PA11

Delivery Form

Powder

Transformation Processes

· Electrostatic spraying

Additives

· Heat Stabilized

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Hardness, Shore D, 23°C (73°F)	- / 71	ISO 868
Hardness, Persoz, 23°C (73°F)	- / 270	ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 17 mg	ISO 9352

*DRY: Dry As Molded (DAM) if pellet / Dry if powder. COND: Conditionned.

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	183-188 °C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181 °C (357.8 °F)	ISO 306



RILSAN® PA11 ESY GREY 7280

OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Covering efficiency (100 µm)	0.20 kg/m²	Internal Arkema
Water absorption, 24h	≤ 1 %	ISO 62
Median particles (D50)	30 µm	ISO 13320
Approximate RAL number	7001	
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Specific gravity of coating, 20°C (68°F)	1.1 g/cm ³	ISO 1183-1
Apparent density, Non compacted	0.44	ISO 1068
Apparent density, Compacted	0.62	ISO 1068
Particle Size Distribution (PSD) (Fine particles < 20 μm)	20 %	ISO 13320
Particle Size Distribution (PSD) (Coarse particles > 100 μm)	1 %	ISO 13320

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

SPECIAL CHARACTERISTICS

Bio-based

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

