

# TECHNICAL DATA SHEET

# **RILSAN® PA11 ESY ORANGE 7705**

#### **POLYAMIDE 11 POWDER**

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® ESY range is designed for coating metal parts using the electrostatic spraying process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations. RILSAN® ESY ORANGE 7705 provides good electrical insulation, even at low thickness. It can be used in electrical applications such as busbar coatings.

#### **DESIGNATION**

PA11

#### **MAIN APPLICATIONS**

• Powder Coating - Electrical Application

#### **DELIVERY FORM**

• Powder

#### **TRANSFORMATION PROCESSES**

• Electrostatic spraying

#### **ADDITIVES**

Heat Stabilized

#### **MECHANICAL PROPERTIES**

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Hardness, Shore D, 23°C (73°F)	- / 71	ISO 868
Hardness, Persoz, 23°C (73°F)	- / 270	ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 25 mg	ISO 9352

<sup>\*</sup>DRY: Dry As Molded (DAM) if pellet / Dry if powder. COND: Conditionned.

## **THERMAL PROPERTIES**

PROPERTIES	VALUE	TEST STANDARD
Vicat softening temperature, 50N at 50°C/h	181 °C	ISO 306
Melting temperature, 10°C/min	183-188 °C (366.8 °F)	ISO 11357-1/-3

## **ELECTRICAL PROPERTIES**

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Dielectric constant, 23°C (73,4°F)	- / 3.7	
Surface resistivity, 23°C (73,4°F)	/ 2.4E+14 ohm/sq	
Comparative tracking index, 23°C (73,4°F)	- / 600	IEC 60112

<sup>\*</sup>DRY: Dry As Molded (DAM) if pellet / Dry if powder. COND: Conditionned.



# RILSAN® PA11 ESY ORANGE 7705

### **OTHER PROPERTIES**

PROPERTIES	VALUE	TEST STANDARD
Covering efficiency (100 µm)	0.12 kg/m²	Internal Arkema
Water absorption, 24h	≤ 1 %	ISO 62
Median particles (D50)	30 µm	ISO 13320
Approximate RAL number	2003	
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Specific gravity of coating, 20°C (68°F)	1.25 g/cm³	ISO 1183-1
Particle Size Distribution (PSD) (Fine particles < 20 μm)	20 %	ISO 13320
Particle Size Distribution (PSD) (Coarse particles > 100 μm)	1 %	ISO 13320
Apparent density, Non compacted	0.44	ISO 1068
Apparent density, Compacted	0.62	ISO 1068

#### **PACKAGING**

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

20 kg / 44 lb bags

### **SHELF LIFE**

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

### **SPECIAL CHARACTERISTICS**

• Bio-based

**Headquarter: Arkema France** 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

