

TECHNICAL DATA SHEET

RILSAN® PA11 MC BLACK 820 MAC

POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® MC range is designed for coating small items using the minicoat/maxicoat process, originally developed by Arkema to allow very high productivity. They provide superior protection against wear, impact, corrosion and chemicals. Please consult Arkema literature for application method and recommendations.

Designation

- PA11

Delivery Form

- Powder

Transformation Processes

- Minicoat / Maxicoat

Additives

- Heat Stabilized

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Hardness, Shore D, 23°C (73°F)	- / 74	ISO 868
Hardness, Persoz, 23°C (73°F)	- / 263	ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 10 mg	ISO 9352

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	183-188 °C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181 °C (357.8 °F)	ISO 306

OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Covering efficiency (100 µm)	0.22 kg/m ²	Internal Arkema
Median particles (D50)	30-60 µm	ISO 13320
Approximate RAL number	9005	
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Specific gravity of coating, 20°C (68°F)	1.12 g/cm ³	ISO 1183-1
Apparent density, Non compacted	0.49	ISO 1068
Apparent density, Compacted	0.67	ISO 1068
Particle Size Distribution (PSD) (Fine particles < 20 µm)	8 %	ISO 13320
Particle Size Distribution (PSD) (Coarse particles > 80 µm)	10 %	ISO 13320

RILSAN® PA11 MC BLACK 820 MAC

SHELF LIFE

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

SPECIAL CHARACTERISTICS

- Bio-based

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA