

## TECHNICAL DATA SHEET

# RILSAN® PA11 MC BLACK 820 MAC

## POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® MC range is designed for coating small items using the minicoat/maxicoat process, originally developed by Arkema to allow very high productivity. They provide superior protection against wear, impact, corrosion and chemicals. Please consult Arkema literature for application method and recommendations.

### DESIGNATION

PA11

### DELIVERY FORM

- Powder

### TRANSFORMATION PROCESSES

- Minicoat / Maxicoat

### ADDITIVES

- Heat Stabilized

## MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	테스트 표준
Hardness, Shore D, 23°C (73°F)	- / 74	ISO 868
Hardness, Persoz, 23°C (73°F)	- / 263	ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 10 mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

속성	값	테스트 표준
Melting temperature, 10°C/min	183-188 °C (366.8 °F)	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181 °C	ISO 306

## OTHER PROPERTIES

속성	값	테스트 표준
Covering efficiency (100 µm)	0.22 kg/m <sup>2</sup>	Internal Arkema
Median particles (D50)	30-60 µm	ISO 13320
Approximate RAL number	9005	
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Specific gravity of coating, 20°C (68°F)	1.12 g/cm <sup>3</sup>	ISO 1183-1
Apparent density, Non compacted	0.49	ISO 1068
Apparent density, Compacted	0.67	ISO 1068
Particle Size Distribution (PSD) (Fine particles < 20 µm)	8 %	ISO 13320
Particle Size Distribution (PSD) (Coarse particles > 80 µm)	10 %	ISO 13320

# RILSAN® PA11 MC BLACK 820 MAC

## PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 21 kg / 44 lb bags

## SHELF LIFE

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## SPECIAL CHARACTERISTICS

- Bio-based

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**