

## TECHNICAL DATA SHEET RILSAN<sup>®</sup> PA11 T BLACK 7450 AC

### POLYAMIDE 11 POWDER

RILSAN<sup>®</sup> fine powders are specialty polyamide powders obtained from renewable resources. RILSAN<sup>®</sup> T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

Designation	Delivery Form
• PA11	• Powder
MAIN APPLICATIONS	Transformation Processes
<ul> <li>Water Fluid Coating - Water Accessories</li> <li>Powder Coating - Renewable Energy</li> <li>Powder Coating - Dish Washer Basket</li> <li>Automotive/Truck - Automotive Coating</li> </ul>	<ul> <li>Fluidized Bed Dipping</li> <li>Additives</li> <li>Heat Stabilized</li> </ul>

### MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Hardness, Shore D, 23°C (73°F)	- / 70	ISO 868
Coating impact, 23°C (73°F)	- / ≥ 2 J	ASTM G14
Hardness, Persoz, 23°C (73°F)	- / 250	ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 13 mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder. COND: Conditionned.

### THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	183-188 °C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181 °C (357.8 °F)	ISO 306



# RILSAN® PA11 T BLACK 7450 AC

### **OTHER PROPERTIES**

PROPERTIES	VALUE	TEST STANDARD
Covering efficiency (300 µm)	0.33 kg/m²	Internal Arkema
Water absorption, 24h	≤ <b>1</b> %	ISO 62
Median particles (D50)	100-130 μm	ISO 13320
Approximate RAL number	9011	
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Specific gravity of coating, 20°C (68°F)	1.05 g/cm <sup>3</sup>	ISO 1183-1
Apparent density, Non compacted	0.52	ISO 1068
Apparent density, Compacted	0.62	ISO 1068
Particle Size Distribution (PSD), Fine particles ( $\leq$ 40 $\mu$ m)	4 %	ISO 13320
Particle Size Distribution (PSD), Coarse particles (> 254 µm)	5 %	ISO 13320

#### 賞味期限

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

### SPECIAL CHARACTERISTICS

Bio-based

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

