

# TECHNICAL DATA SHEET RILSAN® PA11 T BLUE 2682 BHV RX

# **POLYAMIDE 11 POWDER**

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

**DESIGNATION** 

**PA11** 

#### **DELIVERY FORM**

Pellets

#### TRANSFORMATION PROCESSES

· Fluidized Bed Dipping

#### **ADDITIVES**

· Heat Stabilized

# MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	테스트 표준
Hardness, Persoz, 23°C (73°F)	- / 240	ISO 1522
Hardness, Shore D, 23°C (73°F)	- / 70	ISO 868
Coating impact, 23°C (73°F)	-/≥2J	ASTM G14
, Wheel CS 17, load 1 kg, 1000 cycles	- / 15 mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder. COND: Conditionned.

속성 값 테스트 표준

Melting temperature, 10°C/min 183-188 °C (366.8 °F) ISO 11357-1/-3

Vicat softening temperature, 50N at 50°C/h 181 °C ISO 306



# RILSAN® PA11 T BLUE 2682 BHV RX

# OTHER PROPERTIES

속성	값	테스트 표준
Apparent density, Non compacted	0.52	ISO 1068
Apparent density, Compacted	0.62	ISO 1068
Median particles (D50)	100-130 μm	ISO 13320
Particle Size Distribution (PSD), Fine particles (≤ 40 µm)	1 %	ISO 13320
Particle Size Distribution (PSD), Coarse particles (> 254 μm)	7 %	ISO 13320
Covering efficiency (300 µm)	0.36 kg/m²	Internal Arkema
Specific gravity of coating, 20°C (68°F)	1.2 g/cm³	ISO 1183-1
Water absorption, 24h	≤ 1 %	ISO 62
Approximate RAL number	5015	
Salt spray test	Good adhesion after 2000 hours	ISO 9227

# SPECIAL CHARACTERISTICS

Bio-based

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

