

TECHNICAL DATA SHEET
RILSAN® PA11 T BLUE 5019 BVAC

POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

TYPE	배송 방식
PA11	• 분말
MAIN APPLICATIONS	가공 공정
• 자동차/트럭 - 샤프트 도장	• 유동층 침지
• 자동차/트럭 - 자동차 도장	첨가제
	• 열 안정화

MECHANICAL PROPERTIES

속성	DRY / COND VALUE*	UNIT	테스트 표준
Hardness, Shore D, 23°C (73°F)	- / 70		ISO 868
Coating impact, 23°C (73°F)	- / ≥ 2	J	ASTM G14
Hardness, Persoz, 23°C (73°F)	- / 240		ISO 1522
, Wheel CS 17, load 1 kg, 1000 cycles	- / 15	mg	ISO 9352

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

속성	값	UNIT	테스트 표준
Melting temperature, 10°C/min	183-188	°C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181	°C	ISO 306

RILSAN® PA11 T BLUE 5019 BVAC

OTHER PROPERTIES

속성	값	UNIT	테스트 표준
Covering efficiency (300 µm)	0.36	kg/m²	Internal Arkema
Water absorption, 24h	≤ 1	%	ISO 62
Median particles (D50)	100-130	µm	ISO 13320
Approximate RAL number	5015		
Salt spray test	Good adhesion after 2000 hours		ISO 9227
Specific gravity of coating, 20°C (68°F)	1.05	g/cm³	ISO 1183-1
Apparent density, Non compacted	0.52		ISO 1068
Apparent density, Compacted	0.62		ISO 1068
Particle Size Distribution (PSD), Fine particles (≤ 40 µm)	8	%	ISO 13320
Particle Size Distribution (PSD), Coarse particles (> 254 µm)	10	%	ISO 13320

포장

Available packaging:

- 20 kg / 44 lb 가방

보관수명

납품일로부터 5년의 유통기한, 적절히 보관할 때 (밀봉된 봉지, 적절한 습도, 자외선 차단 및 온도). 이 한도를 초과하는 모든 사용에 대해서는 기술 서비스를 참조해 주세요.

특징

- 생물 기반

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80