

### TECHNICAL DATA SHEET

# **RILSAN® PA11 T GREEN 7492 MAC**

### **POLYAMIDE 11 POWDER**

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

DESIGNATION PA11	• Powder
MAIN APPLICATIONS	<ul><li>TRANSFORMATION PROCESSES</li><li>Fluidized Bed Dipping</li></ul>
• Powder Coating - Others	ADDITIVES
	• Heat Stabilized

#### **MECHANICAL PROPERTIES**

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Hardness, Shore D, 23°C (73°F)	- / 74	ISO 868
Coating impact, 23°C (73°F)	- / ≥ 2 J	ASTM G14
Hardness, Persoz, 23°C (73°F)	- / 280	ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 13 mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder. COND: Conditionned.

## THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	183-188 °C (366.8 °F)	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181 °C	ISO 306



# **RILSAN® PA11 T GREEN 7492 MAC**

### **OTHER PROPERTIES**

PROPERTIES	VALUE	TEST STANDARD
Covering efficiency (300 µm)	0.35 kg/m²	Internal Arkema
Water absorption, 24h	≤ 1 %	ISO 62
Median particles (D50)	100-130 μm	ISO 13320
Approximate RAL number	6003	
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Specific gravity of coating, 20°C (68°F)	1.17 g/cm³	ISO 1183-1
Apparent density, Non compacted	0.57	ISO 1068
Apparent density, Compacted	0.69	ISO 1068
Particle Size Distribution (PSD), Fine particles ( $\leq$ 40 $\mu$ m)	1 %	ISO 13320
Particle Size Distribution (PSD), Coarse particles (> 254 $\mu\text{m})$	7 %	ISO 13320

### PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

• 25 kg / 55 lb bags

### SHELF LIFE

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

### **SPECIAL CHARACTERISTICS**

• Bio-based

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

92705 Colombes Cedex - France T +33 (0)1 49 00 80 80

2025-02-17 - Page: 2 / 2