

TECHNICAL DATA SHEET

RILSAN® PA11 T SILVER 7537

POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

TYPE

PA11

MAIN APPLICATIONS

- 粉体塗装 - 食器洗浄機用バスケット

配送形態

- パウダー

変換プロセス

- 流動層浸漬

添加剤

- 熱安定

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	UNIT	テスト基準
Hardness, Shore D, 23°C (73°F)	- / 70		ISO 868
Coating impact, 23°C (73°F)	- / ≥ 2	J	ASTM G14
Hardness, Persoz, 23°C (73°F)	- / 180		ISO 1522
, Wheel CS 17, load 1 kg, 1000 cycles	- / 30	mg	ISO 9352

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

プロパティ	価値	UNIT	テスト基準
Vicat softening temperature, 50N at 50°C/h	181	°C	ISO 306
Melting temperature, 10°C/min	183-188	°C	ISO 11357-1/-3

RILSAN® PA11 T SILVER 7537

OTHER PROPERTIES

プロパティ	価値	UNIT	テスト基準
Covering efficiency (300 µm)	0.36	kg/m²	Internal Arkema
Water absorption, 24h	≤ 1	%	ISO 62
Median particles (D50)	100-130	µm	ISO 13320
Approximate RAL number	9007		
Salt spray test	Good adhesion after 2000 hours		ISO 9227
Specific gravity of coating, 20°C (68°F)	1.01	g/cm³	ISO 1183-1
Apparent density, Non compacted	0.49		ISO 1068
Apparent density, Compacted	0.61		ISO 1068
Particle Size Distribution (PSD), Fine particles (≤ 40 µm)	1	%	ISO 13320
Particle Size Distribution (PSD), Coarse particles (> 254 µm)	7	%	ISO 13320

包装

Available packaging:

- 25 kg / 55 lb 袋

保存期間

納品日から5年間。適切な条件（ 容器の密閉、適切な温度・ 湿度、UVカット ）で保管された場合有効です。この期限を超えて使用する場合は、弊社の技術サービスにご相談ください。

特別な特性

- バイオベース

Headquarter: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com

