

# TECHNICAL DATA SHEET RILSAN® PA11 T SILVER 9108

# **POLYAMIDE 11 POWDER**

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

**DESIGNATION** 

**PA11** 

### **DELIVERY FORM**

Powder

### TRANSFORMATION PROCESSES

• Fluidized Bed Dipping

### **ADDITIVES**

· Heat Stabilized

# **MECHANICAL PROPERTIES**

속성	DRY / COND VALUE*	테스트 표준
Hardness, Shore D, 23°C (73°F)	- / 70	ISO 868
Coating impact, 23°C (73°F)	-/ ≥ <b>2</b> J	ASTM G14
Hardness, Persoz, 23°C (73°F)	- / 180	ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 10 mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.

COND: Conditionned.

속성	값	테스트 표준
Vicat softening temperature, 50N at 50°C/h	181 °C	ISO 306
Melting temperature, 10°C/min	183-188 °C (366.8 °F)	ISO 11357-1/-3



# **RILSAN® PA11 T SILVER 9108**

## OTHER PROPERTIES

속성	값	테스트 표준
Covering efficiency (300 µm)	0.36 kg/m²	Internal Arkema
Water absorption, 24h	≤ 1 %	ISO 62
Median particles (D50)	100-130 µm	ISO 13320
Approximate RAL number	9023	
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Median particles (D50)	100-130 μm	ISO 13320
Specific gravity of coating, 20°C (68°F)	1.03 g/cm³	ISO 1183-1
Particle Size Distribution (PSD), Fine particles (≤ 40 μm)	1 %	ISO 13320
Particle Size Distribution (PSD), Coarse particles (> 254 μm)	7 %	ISO 13320
Apparent density, Non compacted	0.50	ISO 1068
Apparent density, Compacted	0.61	ISO 1068

## **PACKAGING**

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

• 851 kg / 1870 lb rigid containers

### SHELF LIFE

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## SPECIAL CHARACTERISTICS

• Bio-based

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

