

# TECHNICAL DATA SHEET

# **RILSAN® PA11 T WHITE 1482**

# **POLYAMIDE 11 POWDER**

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

DESIGNATION PA11	• Powder
MAIN APPLICATIONS	TRANSFORMATION PROCESSES     Fluidized Bed Dipping
<ul> <li>Water Fluid Coating - Water Accessories</li> <li>Water Fluid Coating - Piping Systems</li> <li>Powder Coating - Dish Washer Basket</li> <li>Powder Coating- Wire Goods</li> </ul>	ADDITIVES • Heat Stabilized

#### **MECHANICAL PROPERTIES**

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Hardness, Shore D, 23°C (73°F)	- / 71	ISO 868
Coating impact, 23°C (73°F)	- / ≥ 2 J	ASTM G14
Hardness, Persoz, 23°C (73°F)	- / 260	ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 12 mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.

#### COND: Conditionned.

#### **THERMAL PROPERTIES**

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	183-188 °C (366.8 °F)	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181 °C	ISO 306

# **OTHER PROPERTIES**

PROPERTIES	VALUE	TEST STANDARD
Covering efficiency (300 μm)	0.36 kg/m²	Internal Arkema
Water absorption, 24h	≤ 1 %	ISO 62
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Specific gravity of coating, 20°C (68°F)	1.1 g/cm <sup>3</sup>	ISO 1183-1
Median particles (D50)	100-130 µm	ISO 13320
Particle Size Distribution (PSD), Fine particles (≤ 40 $\mu m)$	1 %	ISO 13320
Particle Size Distribution (PSD), Coarse particles (> 254 µm)	3 %	ISO 13320
Apparent density, Non compacted	0.55	ISO 1068
Apparent density, Compacted	0.66	ISO 1068



# PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging: • 25 kg / 55 lb bags

# SHELF LIFE


Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

# **SPECIAL CHARACTERISTICS**

• Bio-based

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

ARKEMA



arkema.com