

TECHNICAL DATA SHEET RILSAN® PA11 T WHITE 1482

POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

TYPE

PA11

MAIN APPLICATIONS

- · Water Fluid Coating Water Accessories
- Water Fluid Coating Piping Systems
- Powder Coating Dish Washer Basket
- · Powder Coating- Wire Goods

DELIVERY FORM

Powder

TRANSFORMATION PROCESSES

· Fluidized Bed Dipping

ADDITIVES

· Heat Stabilized

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	UNIT	テスト基準
Hardness, Shore D, 23°C (73°F)	- / 71		ISO 868
Coating impact, 23°C (73°F)	-/≥2	J	ASTM G14
Hardness, Persoz, 23°C (73°F)	- / 260		ISO 1522
, Wheel CS 17, load 1 kg, 1000 cycles	- / 12	mg	ISO 9352

^{*}DRY: Dry As Molded (DAM) if pellet / Dry if powder. COND: Conditionned.

THERMAL PROPERTIES

プロパティ	価値	UNIT	テスト基準
Melting temperature, 10°C/min	183-188	°C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181	°C	ISO 306



RILSAN® PA11 T WHITE 1482

OTHER PROPERTIES

プロパティ	価値	UNIT	テスト基準
Covering efficiency (300 µm)	0.36	kg/m²	Internal Arkema
Water absorption, 24h	≤ 1	%	ISO 62
Salt spray test	Good adhesion after 2000 hours		ISO 9227
Specific gravity of coating, 20°C (68°F)	1.1	g/cm³	ISO 1183-1
Median particles (D50)	100-130	μm	ISO 13320
Particle Size Distribution (PSD), Fine particles (≤ 40 µm)	1	%	ISO 13320
Particle Size Distribution (PSD), Coarse particles (> 254 µm)	3	%	ISO 13320
Apparent density, Non compacted	0.55		ISO 1068
Apparent density, Compacted	0.66		ISO 1068

包装

Available packaging:

• 25 kg / 55 lb 袋

賞味期限

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

SPECIAL CHARACTERISTICS

Bio-based

Headquarter: Arkema France 51, Esplanade du Général de Gaulle 92800 Puteaux – France T +33 (0)1 49 00 80 80

