

TECHNICAL DATA SHEET

RILSAN® PA11 T WHITE 1488 AC

POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

TYPE

PA11

MAIN APPLICATIONS

- Water Fluid Coating - Piping Systems
- Powder Coating- Wire Goods
- Automotive/Truck - Automotive Coating

DELIVERY FORM

- Powder

TRANSFORMATION PROCESSES

- Fluidized Bed Dipping

ADDITIVES

- Heat Stabilized

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	UNIT	TEST STANDARD
Hardness, Persoz, 23°C (73°F)	- / 240		ISO 1522
Hardness, Shore D, 23°C (73°F)	- / 79		ISO 868
Coating impact, 23°C (73°F)	- / ≥ 2	J	ASTM G14
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 13	mg	ISO 9352

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Melting temperature, 10°C/min	183-188	°C	ISO 11357-1/-3
Vicat softening temperature, 50N at 50°C/h	181	°C	ISO 306

RILSAN® PA11 T WHITE 1488 AC

OTHER PROPERTIES

PROPERTIES	VALUE	UNIT	TEST STANDARD
Median particles (D50)	100-130	µm	ISO 13320
Apparent density, Non compacted	0.55		ISO 1068
Apparent density, Compacted	0.66		ISO 1068
Approximate RAL number	9010		
Covering efficiency (300 µm)	0.35	kg/m²	Internal Arkema
Particle Size Distribution (PSD), Fine particles (≤ 40 µm)	1	%	ISO 13320
Particle Size Distribution (PSD), Coarse particles (> 254 µm)	4	%	ISO 13320
Water absorption, 24h	≤ 1	%	ISO 62
Salt spray test	Good adhesion after 2000 hours		ISO 9227
Specific gravity of coating, 20°C (68°F)	1.17	g/cm³	ISO 1183-1

PACKAGING

Available packaging:

- 25 kg / 55 lb bags

SHELF LIFE

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

SPECIAL CHARACTERISTICS

- Bio-based

Headquarters: Arkema France
51, Esplanade du Général de Gaulle
92800 Puteaux – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790