

TECHNICAL DATA SHEET

RILSAN® PA11 T WHITE 1488

POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

DESIGNATION

PA11

MAIN APPLICATIONS

- Water Fluid Coating - Piping Systems
- Powder Coating- Wire Goods
- Automotive/Truck - Automotive Coating

DELIVERY FORM

- Powder

TRANSFORMATION PROCESSES

- Fluidized Bed Dipping

ADDITIVES

- Heat Stabilized

MECHANICAL PROPERTIES

| プロパティ | DRY / COND VALUE* | テスト基準 |
|--|-------------------|----------|
| Hardness, Persoz, 23°C (73°F) | - / 240 | ISO 1522 |
| Hardness, Shore D, 23°C (73°F) | - / 79 | ISO 868 |
| Coating impact, 23°C (73°F) | - / ≥ 2 J | ASTM G14 |
| Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles | - / 13 mg | ISO 9352 |

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditionned.

THERMAL PROPERTIES

| プロパティ | 価値 | テスト基準 |
|--|-----------------------|----------------|
| Melting temperature, 10°C/min | 183-188 °C (366.8 °F) | ISO 11357-1/-3 |
| Vicat softening temperature, 50N at 50°C/h | 181 °C | ISO 306 |

RILSAN® PA11 T WHITE 1488

OTHER PROPERTIES

| プロパティ | 価値 | テスト基準 |
|---|--------------------------------|-----------------|
| Median particles (D50) | 100-130 µm | ISO 13320 |
| Apparent density, Non compacted | 0.55 | ISO 1068 |
| Apparent density, Compacted | 0.66 | ISO 1068 |
| Approximate RAL number | 9010 | |
| Covering efficiency (300 µm) | 0.35 kg/m ² | Internal Arkema |
| Particle Size Distribution (PSD), Fine particles (≤ 40 µm) | 1 % | ISO 13320 |
| Particle Size Distribution (PSD), Coarse particles (> 254 µm) | 4 % | ISO 13320 |
| Water absorption, 24h | ≤ 1 % | ISO 62 |
| Salt spray test | Good adhesion after 2000 hours | ISO 9227 |
| Specific gravity of coating, 20°C (68°F) | 1.17 g/cm ³ | ISO 1183-1 |

包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

賞味期限

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

SPECIAL CHARACTERISTICS

- Bio-based

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA