

### TECHNICAL DATA SHEET

## **RILSAN® PA11 T WHITE 7279S**

#### **POLYAMIDE 11 POWDER**

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

Designation	Delivery Form
• PA11	• Powder
MAIN APPLICATIONS	<b>Transformation Processes</b>
• Powder Coating - Undergarment	• Fluidized Bed Dipping
	Additives
	• Heat Stabilized

#### **MECHANICAL PROPERTIES**

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Hardness, Shore D, 23°C (73°F)	- / 74	ISO 868
Coating impact, 23°C (73°F)	- / ≥ 2 J	ASTM G14
Hardness, Persoz, 23°C (73°F)	- / 225	ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 30 mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.

COND: Conditionned.

#### **THERMAL PROPERTIES**

PROPERTIES	VALUE	TEST STANDARD
Vicat softening temperature, 50N at 50°C/h	181 °C (357.8 °F)	ISO 306
Melting temperature, 10°C/min	183-188 °C	ISO 11357-1/-3



# RILSAN® PA11 T WHITE 72795

#### **OTHER PROPERTIES**

PROPERTIES	VALUE	TEST STANDARD
Covering efficiency (300 µm)	0.36 kg/m²	Internal Arkema
Water absorption, 24h	≤ 1 %	ISO 62
Specific gravity		
Median particles (D50)	100-130 μm	ISO 13320
Approximate RAL number	9010	
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Apparent density, Non compacted	0.54	ISO 1068
Apparent density, Compacted	0.66	ISO 1068
Particle Size Distribution (PSD), Coarse particles (> 254 µm)	3 %	ISO 13320
Particle Size Distribution (PSD), Fine particles (≤ 40 $\mu$ m)	2 %	ISO 13320
Specific gravity of coating, 20°C (68°F)	1.1 g/cm³	ISO 1183-1

#### SHELF LIFE

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

#### **SPECIAL CHARACTERISTICS**

• Bio-based

2025-01-17 - Page: 2 / 2

ЧЧН

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

