

## TECHNICAL DATA SHEET

# RILSAN® PA11 T WHITE 7279S

## POLYAMIDE 11 POWDER

RILSAN® fine powders are specialty polyamide powders obtained from renewable resources. RILSAN® T range is designed for coating metal parts using the fluidized bed dip coating process. They provide superior protection against wear, impact, corrosion, chemicals as well as graffiti. Please consult Arkema literature for application method and recommendations.

### Designation

- PA11

### MAIN APPLICATIONS

- Powder Coating - Undergarment

### Delivery Form

- Powder

### Transformation Processes

- Fluidized Bed Dipping

### Additives

- Heat Stabilized

## MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Hardness, Shore D, 23°C (73°F)	- / 74	ISO 868
Coating impact, 23°C (73°F)	- / ≥ 2 J	ASTM G14
Hardness, Persoz, 23°C (73°F)	- / 225	ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 30 mg	ISO 9352

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditionned.

## THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Vicat softening temperature, 50N at 50°C/h	181 °C (357.8 °F)	ISO 306
Melting temperature, 10°C/min	183-188 °C	ISO 11357-1/-3

# RILSAN® PA11 T WHITE 7279S

## OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Covering efficiency (300 µm)	0.36 kg/m <sup>2</sup>	Internal Arkema
Water absorption, 24h	≤ 1 %	ISO 62
Specific gravity		
Median particles (D50)	100-130 µm	ISO 13320
Approximate RAL number	9010	
Salt spray test	Good adhesion after 2000 hours	ISO 9227
Apparent density, Non compacted	0.54	ISO 1068
Apparent density, Compacted	0.66	ISO 1068
Particle Size Distribution (PSD), Coarse particles (> 254 µm)	3 %	ISO 13320
Particle Size Distribution (PSD), Fine particles (≤ 40 µm)	2 %	ISO 13320
Specific gravity of coating, 20°C (68°F)	1.1 g/cm <sup>3</sup>	ISO 1183-1

## 賞味期限

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

## SPECIAL CHARACTERISTICS

- Bio-based

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**