

TECHNICAL DATA SHEET RILSAN® PA11 TECHLINE WHITE 7601

POLYAMIDE 11 POWDER

RILSAN® minicoat/ maxicoat powders are thermoplastic polyamides obtained from renewable resources.

Outstanding characteristics: abrasion resistance, corrosion resistance, impact resistance, sound reduction, flexibility, low coefficient of friction.

DESIGNATION

PA11

MAIN APPLICATIONS

· Powder Coating - Undergarment

DELIVERY FORM

Powder

TRANSFORMATION PROCESSES

• Fluidized Bed Dipping

ADDITIVES

Heat Stabilized

MECHANICAL PROPERTIES

プロパティ	DRY / COND VALUE*	テスト基準
Hardness, Persoz, 23°C (73°F)	- / 270	ISO 1522
Abrasion resistance, Wheel CS 17, load 1 kg, 1000 cycles	- / 8 mg	ISO 9352

^{*}DRY: Dry As Molded (DAM) if pellet / Dry if powder. COND: Conditionned.

THERMAL PROPERTIES

プロパティ	価値	テスト基準
Melting temperature, 10°C/min	183-188 °C (366.8 °F)	ISO 11357-1/-3



RILSAN® PA11 TECHLINE WHITE 7601

OTHER PROPERTIES

プロパティ	価値	テスト基準
Apparent density, Non compacted	0.44	ISO 1068
Apparent density, Compacted	0.57	ISO 1068
Specific gravity of coating, 20°C (68°F)	1.11 g/cm³	ISO 1183-1
Median particles (D50)	30-60 μm	ISO 13320
Particle Size Distribution (PSD) (Coarse particles > 80 μm)	6 %	ISO 13320
Particle Size Distribution (PSD) (Fine particles < 20 μm)	10 %	ISO 13320
Water absorption, 24h	≤ 1 %	ISO 62
Approximate RAL number	9016	
Covering efficiency (200 µm)	0.22 kg/m²	Internal Arkema
Salt spray test	Good adhesion after 2000 hours	ISO 9227

包装

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

20 kg / 44 lb bags

賞味期限

Five years shelf life from date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

SPECIAL CHARACTERISTICS

Bio-based

Headquarter: Arkema France 420, rue d'Estienne d'Orves 92705 Colombes Cedex – France T +33 (0)1 49 00 80 80

