

## TECHNICAL DATA SHEET

# RILSAN® ROTO 11 NATURAL

## POLYAMIDE 11 POWDER

RILSAN® ROTO 11 NATURAL is a polyamide 11 powder. It is produced from a renewable & sustainable source (castor oil). This grade is designed for roto molding.

**Designation :** ISO 16396 - PA11-P, RDHL, C12-010

### DESIGNATION

PA11-P

### MAIN APPLICATIONS

- Heavy Truck H2 & Gas Lines And Tanks

### DELIVERY FORM

- Pellets

### TRANSFORMATION PROCESSES

- Rotomolding

### ADDITIVES

- Plasticizer

## MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Yield strain, 23°C (73°F), 50 mm/min	- / 31 %	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 43 MPa	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	- / 965 MPa	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	- / 7.5 kJ/m2	ISO 179 1eA
Stress at break	- / 37 MPa	ISO 527-1/-2
Strain at break	- / > 50 %	ISO 527-1/-2

\*DRY: Dry As Molded (DAM) if pellet / Dry if powder.  
COND: Conditioned.

## THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	185 °C	ISO 11357-1/-3

## OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Specific gravity, 23°C (73°F)	1.05 g/cm <sup>3</sup>	ISO 1183-1

## PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 45 kg / 100 lb drums

## SHELF LIFE



Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

# RILSAN® ROTO 11 NATURAL

## SPECIAL CHARACTERISTICS

- Bio-based

## DIAGRAMS



**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.  
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

arkema.com

**ARKEMA**