

TECHNICAL DATA SHEET

RILSAN® TIEFLEX S452 NAT T6L

POLYAMIDE ALLOY PELLET

RILSAN® TIEFLEX S452 NAT T6L is a polyamide alloy. It is partially produced from a renewable & sustainable source (castor oil). This grade is designed for multilayer automotive and trucks fuel lines (structural tie layer).

DESIGNATION

PA*

MAIN APPLICATIONS

- Auto - In Tank & Fuel Venting Lines

DELIVERY FORM

- Pellets

TRANSFORMATION PROCESSES

- Extrusion - General
- Tube Extrusion

ADDITIVES

- Heat Stabilized
- Light Stabilized
- Plasticizer

RHEOLOGICAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melt volume flow rate (MVR), 235°C / 5 kg (455°F / 11 lb)	3.7 cm ³ /10min	ISO 1133

MECHANICAL PROPERTIES

PROPERTIES	DRY / COND VALUE*	TEST STANDARD
Tensile modulus, 23°C (73°F), 1 mm/min	685 / 515 MPa	ISO 527-1/-2
Yield stress, 23°C (73°F), 50 mm/min	- / 33 MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	- / 31 %	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	- / 25 %	ISO 527-1/-2
Charpy unnotched impact strength, 23°C (73°F)	- / No Break	ISO 179 1eU
Charpy unnotched impact strength, -30°C (-22°F)	- / No Break	ISO 179 1eU
Charpy notched impact strength, 23°C (73°F)	- / 95 kJ/m ²	ISO 179 1eA
Charpy notched impact strength, -30°C (-22°F)	- / 6.5 kJ/m ²	ISO 179 1eA

*DRY: Dry As Molded (DAM) if pellet / Dry if powder.
COND: Conditioned.

THERMAL PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Melting temperature, 10°C/min	217 °C	ISO 11357-1/-3

RILSAN® TIEFLEX S452 NAT T6L

OTHER PROPERTIES

PROPERTIES	VALUE	TEST STANDARD
Specific gravity, 23°C (73°F)	1.09 g/cm ³	ISO 1183-1
Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR	1.2 %	ISO 62
Water absorption, 23°C (73°F), immersion, equilibrium	2.9 %	ISO 62

PACKAGING

This grade is delivered dried in sealed packaging ready to be processed. Available packaging:

- 25 kg / 55 lb bags

SHELF LIFE

Two years from the date of delivery, when stored properly (sealed bags, appropriate moisture, UV protection and temperature). For any use above this limit, please refer to our technical services.

PROCESSING CONDITIONS:

- Typical melt temperature (Min / Recommended / Max) - Injection Molding: 250°C / 270°C / 290°C (480°F / 520°F / 555°F)
- Typical mold temperature - Injection molding: 20-60°C (70-140°F)
- Drying time and temperature: 80-90°C (175-195°F) / 4-6 hours

SPECIAL CHARACTERISTICS

- Bio-based

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA