

TECHNICAL DATA SHEET

VOLTALEF® 302 POWDER

FLUORINATED HOMOPOLYMER POWDER

VOLTALEF® 302 POWDER resin is a fluorinated polymer which presents an exceptional behavior at very low temperatures. It is usable in continuation from -200°C to +150°C with allowable peaks at 200°C. It is non-inflammability, has excellent chemical and radiation resistance, good barrier properties, is insensitivity to oxygen and water with good electrical properties. The processing is critical but can be done by extrusion, injection and compression molding.

DESIGNATION

PCTFE

MAIN APPLICATIONS

- Internal Components
- Aerospace
- Hi Purity
- Molding

TRANSFORMATION PROCESSES

- Film Extrusion
- Injection Molding
- Other Extrusion
- Transfer Molding

MECHANICAL PROPERTIES

| プロパティ | 価値 | テスト基準 |
|---|----------------------|--------------|
| Nominal strain at break, 23°C (73°F), 50 mm/min | 50 % | ISO 527-1/-2 |
| Charpy notched impact strength, 23°C (73°F) | 80 kJ/m ² | ISO 179 1eA |
| Yield stress, 23°C (73°F), 50 mm/min | 43 MPa | ISO 527-1/-2 |
| Yield strain, 23°C (73°F), 50 mm/min | 7 % | ISO 527-1/-2 |
| Nominal strain at break, 23°C (73°F), 50 mm/min | 23 % | ISO 527-1/-2 |
| Yield strain, 23°C (73°F), 50 mm/min | 7 % | ISO 527-1/-2 |
| Tensile modulus, 23°C (73°F), 1 mm/min | 1400 MPa | ISO 527-1/-2 |

THERMAL PROPERTIES

| プロパティ | 価値 | テスト基準 |
|--|--------|----------------|
| Glass transition temperature, 10°C/min | 55 °C | ISO 11357-1/-2 |
| Heat deflection temperature, 1.8 MPa | 70 °C | ISO 75-1/-2 |
| Heat deflection temperature, 0.45 MPa | 126 °C | ISO 75-1/-2 |
| Oxygen index | 100 % | ISO 4589-1/-2 |
| Melting temperature, 10°C/min | 214 °C | ISO 11357-1/-3 |

VOLTALEF® 302 POWDER

ELECTRICAL PROPERTIES

| プロパティ | 価値 | テスト基準 |
|------------------------------------|----------------|-------------|
| Surface resistivity | 1*10E15 ohm/sq | |
| Volumic (transversal) resistivity | 2*10E12 ohm*m | |
| Dielectric strength, 23°C (73,4°F) | 21 kV/mm | IEC 60243-1 |

OTHER PROPERTIES

| プロパティ | 価値 | テスト基準 |
|--|------------|--------|
| Water absorption, Saturated in water at 23°C (73°F) | 0.01 % | ISO 62 |
| Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR | 0.01 % | ISO 62 |
| Apparent density, Non compacted | 2130 kg/m³ | |

SPECIAL CHARACTERISTICS

- Flame & smoke

REGIONAL AVAILABILITY

Africa, Asia Pacific, Europe, Latin America and the Caribbean, Northern America

Headquarter: Arkema France
420, rue d'Estienne d'Orves
92705 Colombes Cedex – France
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.
Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

ARKEMA