

## TECHNICAL DATA SHEET

# VOLTALEF® 302 POWDER

## FLUORINATED HOMOPOLYMER POWDER

VOLTALEF® 302 POWDER resin is a fluorinated polymer which presents an exceptional behavior at very low temperatures. It is usable in continuation from -200°C to +150°C with allowable peaks at 200°C. It is non-inflammability, has excellent chemical and radiation resistance, good barrier properties, is insensitivity to oxygen and water with good electrical properties. The processing is critical but can be done by extrusion, injection and compression molding.

### DESIGNATION

PCTFE

### TRANSFORMATION PROCESSES

- Film Extrusion
- Injection Molding
- Other Extrusion
- Transfer Molding

## MECHANICAL PROPERTIES

속성	값	테스트 표준
Nominal strain at break, 23°C (73°F), 50 mm/min	50 %	ISO 527-1/-2
Charpy notched impact strength, 23°C (73°F)	80 kJ/m <sup>2</sup>	ISO 179 1eA
Yield stress, 23°C (73°F), 50 mm/min	43 MPa	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	7 %	ISO 527-1/-2
Nominal strain at break, 23°C (73°F), 50 mm/min	23 %	ISO 527-1/-2
Yield strain, 23°C (73°F), 50 mm/min	7 %	ISO 527-1/-2
Tensile modulus, 23°C (73°F), 1 mm/min	1400 MPa	ISO 527-1/-2
속성	값	테스트 표준
Glass transition temperature, 10°C/min	55 °C	ISO 11357-1/-2
Heat deflection temperature, 1.8 MPa	70 °C	ISO 75-1/-2
Heat deflection temperature, 0.45 MPa	126 °C	ISO 75-1/-2
Oxygen index	100 %	ISO 4589-1/-2
Melting temperature, 10°C/min	214 °C	ISO 11357-1/-3

## THERMAL PROPERTIES/ELECTRICAL PROPERTIES

속성	값	테스트 표준
Surface resistivity	1*10E15 ohm/sq	
Volumic (transversal) resistivity	2*10E12 ohm*m	
Dielectric strength, 23°C (73,4°F)	21 kV/mm	IEC 60243-1

# VOLTALEF® 302 POWDER

## OTHER PROPERTIES

속성	값	테스트 표준
Water absorption, Saturated in water at 23°C (73°F)	0.01 %	ISO 62
Moisture absorption, At equilibrium at 23°C (73°F) / 50%HR	0.01 %	ISO 62
Apparent density, Non compacted	2130 kg/m <sup>3</sup>	

## SPECIAL CHARACTERISTICS

- Flame & smoke

**Headquarter: Arkema France**  
420, rue d'Estienne d'Orves  
92705 Colombes Cedex – France  
T +33 (0)1 49 00 80 80

Disclaimer - Please consult Arkema's disclaimer regarding the use of Arkema's products on <https://www.arkema.com/global/en/products/product-safety/disclaimer/> which is incorporated herein by reference and made a part hereof.

Arkema France, a French société anonyme registered at the Trade and Companies Register of Nanterre under the number 319 632 790

[arkema.com](https://www.arkema.com)

**ARKEMA**